

Certificate of Analysis



Clearsafe Environmental Solutions Pty Ltd

9 Industrial Road, Unanderra NSW 2526

info@clearsafe.com.au

1300 042 962

Report Number: 20-9006-04-ID

Date of Report: 17/6/2019

Date of Analysis: 17/6/2019

Site Address: Asbestos Analysis

As received

Client Contact: Andrea Waddell

Client Name: Technos Pty Ltd

Sampled By: As Received

Client Address: 71 McClure Street

Approved Identifier: Nathan Crouch

Thornbury Victoria 3071

Approved Signatory: Luke Heckenberg

Test Method: Asbestos identification in bulk samples by polarised light microscopy and dispersion staining, in accordance with 'AS4964-2004 Method for the Qualitative Identification of Asbestos in Bulk Samples' and Clearsafe Method SOP.ID.01 [Detection Limit - 0.1g/kg (AS4964)].

Notes: The results contained within this report relate only to the samples tested. This report should not be copied, presented or reviewed except in full.

An independent analytical technique is recommended for confirmation of vinyl and bituminous samples, or samples in which 'Unknown Mineral Fibre' is detected.

NATA accreditation relates to the analysis of the sample(s) and does not cover the sample collection process.

Sample Number	Sample Reference / Location	Description **	Result *
20-9006/5	Wire Gauze Mat with Ceramic Centre - Supplier No. 1	White Ceramic Material, No Visible Fibres. Sample Size: 150x150x2mm	No Asbestos Detected
20-9006/6	Wire Gauze Mat with Ceramic Centre - JMD Inhouse	White Ceramic Material, No Visible Fibres. Sample Size: 150x150x2mm	No Asbestos Detected

*** Result Codes:**

- 1 - Chrysotile Asbestos Detected
- 2 - Amosite Asbestos Detected
- 3 - Crocidolite Asbestos Detected
- 4 - Unknown Mineral Fibre Detected
- 5 - Synthetic Mineral Fibre (SMF) Present
- 6 - Organic Fibres Present

**** Description Codes:**

- FCS - Fibrous Cement Sheeting
- VFT - Vinyl Floor Tile

20-9006-04-ID



NATA Accredited Laboratory No. 18542

Accredited for compliance with ISO/IEC 17025 - Testing. The results of the tests, calibrations and/or measurements included in this document are traceable to Australian / national standards.